

## Ryeflow 2000 & 3000



### Epoxy Flooring - FeRFA Type 5

Flow applied flooring – 2mm to 3mm

#### Description

Ryeflow is a medium to heavy duty epoxy resin floor finish providing a smooth, easily cleaned surface with excellent resistance to chemicals. The smooth finish is obtained by finishing and smoothing the surface with a specially designed Ryebrook spiked roller. The incorporation of abrasion resistant fillers in the epoxy resin produces a floor finish with the highest order of wear resistance.

Three different products are available which use variable levels of fillers to enable Ryeflow to be applied at thicknesses from 2.0-3.0mm. Ryeflow 2000 2.0-2.5mm | Ryeflow 3000 2.5-4.0mm

#### ADVANTAGES & BENEFITS

- ✓ Highest order of abrasion resistance
- ✓ Easily cleaned and maintained

#### TYPICAL AREA OF USE

- ✓ Storage areas
- ✓ Dry processing
- ✓ Engineering
- ✓ Laboratories
- ✓ Clean rooms
- ✓ Trucking routes
- ✓ Warehousing
- ✓ Showrooms
- ✓ Retail

#### TECHNICAL DATA (N/mm<sup>2</sup>)

	2000	3000
Compressive Strength	38	42
Flexural Strength	30	32
Tensile Strength	25	25
Slant Shear Bond Strength	29	29
Density	1.65	1.9
Elastics Modulus	3	3
Flame Spread (BS476 Part 7)	Class 2	Class 2
Therma Cycle...		
Ease of Decontamination to BS4247 Part 1 Test A	Excellent	Excellent
Slip Potential	High - Medium	High - Medium

#### Composition

3 pack solvent free epoxy resin and graded quartz aggregates.

#### Appearance

Smooth gloss coloured finish.

#### Chemical Resistance

Ryeflow treated surface exhibits excellent resistant to a wide range of chemicals including Skydrol. Please refer to technical data sheet reference TD112.

#### Durability

Ryeflow exhibits the highest order of abrasion resistance.

#### Thickness

2.0 – 3.0mm

#### Colours Available

A range of colour choices are available, please contact our Sales Team for a colour chart.

## Ryeflow

### Substrates

Ryeflow adheres well to concrete, screed and grano.

### Coverage Rates

Ryeflow	2000	3000
Nominal Thickness	2.0mm	3.0mm
Coverage kg/m <sup>2</sup>	3.6	5.4

### Surface Preparation

To be assured of maximum adhesion and properties from Ryebrook resin products, the correct surface preparation is essential. Please refer to technical data sheet "Surface Preparation" reference TD102.

### Application Conditions

Ryeflow is a free flowing liquid which increases in viscosity as the temperature lowers. To ensure optimum finish an ambient temperature in excess of 10°C should be provided. Ideal application temperatures 15°C.

### Priming

Ryepime SF at 125g/m<sup>2</sup>. Allow to cure prior to application of Ryeflow.

### Mixing

The use of a rotary drum mixer is essential to produce a smooth even finish. Mix the resin and hardener units together thoroughly with a slow speed paddle mixer for at least 60 seconds until even coloured. Then add the Ryeflow aggregate slowly whilst mixing at the same time. Allow to mix for further 3 minutes.

### Application Technique

This product is laid in compliance with BS 8204-6 Type 5. Spread the mixed Ryeflow to required thickness using a trowel and level using a Ryebrook spiked roller. Depending on the temperature it may be necessary to use the spiked roller after 15-30 minutes to ensure that all the air has been released.

### Specification Detail

Ryepime SF to prime at 125g/m<sup>2</sup>. Ryeflow at coverage rates described.

### Cure Schedule

Pot Life	30 mins
Initial Set	8-10 hours
Foot Traffic	24 hours
Heavy Traffic	3-4 days
Full Chemical Resistance	7-10 days

### Maintenance

Providing contamination is not allowed to build up, regular scrubbing and mopping will maintain Ryeflow floors satisfactorily. Ryeflow floors may be polished back to the original gloss in exactly the same way as vinyl or lino.

### Health and Safety

Please read technical data sheet reference TD103 and specific health and safety data for this product provided in compliance with the requirements of EC Directive 91/155.

### Storage, Mixing and Application

The storage, mixing and application conditions can affect the quality of the finish produced. Please read technical data sheet reference TD104.

### Further Technical Advice

For further information on this or any other Ryebrook product, please contact our Technical Department on 01634 957520 or email [info@ryebrook.co.uk](mailto:info@ryebrook.co.uk)